

PRL PC/TP-FR2Units English ▼Polymer Resources Ltd. - *Polycarbonate + Polyester***Action** **Legend** ([Open](#))**General Information**

General	
Material Status	• Commercial: Active
Availability	• North America
Additive	• Flame Retardant • Impact Modifier
Features	• Chemical Resistant • Impact Modified • Ultra High Impact Resistance • Flame Retardant • Low Temperature Impact Resistance • Good Weather Resistance • Self Extinguishing
RoHS Compliance	• RoHS Compliant
UL File Number	• E113219
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.25		ASTM D792
Melt Mass-Flow Rate (MFR) (265°C/2.16 kg)	5.0 to 12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	6.0E-3 to 9.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 0.125 in)	7300	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	7000	psi	ASTM D638
Flexural Modulus (0.125 in)	290000	psi	ASTM D790
Flexural Strength (0.125 in)	11000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°F, 0.125 in	7.0	ft·lb/in	
73°F, 0.125 in	13	ft·lb/in	
Gardner Impact (0.125 in)	320	in·lb	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	195	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	180	°F	ASTM D648
RTI Elec (0.06 in)	167	°F	UL 746B
RTI Imp (0.06 in)	167	°F	UL 746B
RTI Str (0.06 in)	167	°F	UL 746B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	220 to 230	°F
Drying Time	4.0 to 6.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	480 to 520	°F
Middle Temperature	490 to 530	°F
Front Temperature	500 to 540	°F
Processing (Melt) Temp	475 to 525	°F
Mold Temperature	150 to 190	°F

Notes¹ Typical properties: these are not to be construed as specifications.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.